

**GLOBALPRENE 7551 Styrene-Ethylene/Butylene block copolymer 苯乙烯-乙烯/丁烯嵌段共聚物**

<b>Features 特性 :</b>		<b>Typical Application 一般應用 :</b>			
• Linear and clear block copolymer	線狀透明嵌段共聚物	• Plastic modification	塑料改質		
• Excellent weather and heat resistance	優良的耐候性及耐熱性	• Adhesives	黏著劑		
• High mechanical strength	高機械強度	• Compounding for modification	混鍊改質		
• Good compatibility with plastics	與塑膠有好的相容性	• Toys	玩具		
		• Asphalt modification	瀝青改質		
<b>Typical Properties :</b>		<b>Test Method</b>	<b>Unit</b>	<b>Value</b>	<b>Range</b>
<b>一般性質</b>		<b>測試方法</b>	<b>單位</b>	<b>數值</b>	<b>範圍</b>
<b>SM Content 苯乙烯含量</b>		ASTM D5775	%	33	31.5~34.5
<b>Specific Gravity 比重</b>		ASTM D792	g/cc	0.91	≥0.91
<b>Volatile Matter 揮發份</b>		ASTM D5668	%	0.2	≤0.5
<b>Ash Content 灰份</b>		ASTM D5667	%	0.6	≤1.0
<b>10wt% / 25°C Toluene Viscosity 10wt% / 25°C 甲苯黏度</b>		ASTM D2196	cP	2000	1300~2700

Note : SM content is measured on polymer before hydrogenation. 苯乙烯含量為氫化前測量值

Packing 包裝: 13kg PE bag 13 公斤 PE 袋

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

符合美國食品及藥物管理局 21 CFR 177.1810(b)(3)之規範

Comply with FDA CFR 177.1810(b)(3)

**Product Stewardship Information 產品責任資訊**

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值· 唯因使用時加工條件及環境之不同· 而產生之差異非本公司所能保證與控制。

商務服務處 Sales Services	台灣 台北市松山區八德路四段 85 號 3 樓 3F., No.85, Sec. 4, Bade Rd., Songshan Dist., Taipei City 105, Taiwan	Tel : +886-2-27631611 Fax : +886-2-27482661
環球橡膠股份有限公司 LCY GRIT CORP.	台灣 高雄市小港區中林路 16 號 No.16, Zhonglin Rd., Xiaogang Dist., Kaohsiung City 812, Taiwan	Tel : +886-7-8712268 Fax : +886-7-8712296
惠州李長榮橡膠有限公司	中國 廣東省惠州市大亞灣經濟技術開發區石化區石化大道中 299 號 No.299 Shihua Dadaozhong, Dayawan Economic & Technological Development Zone, Huizhou, Guangdong, 516082, P.R.C.	Tel : +86-752-5599000 Fax : +86-752-5599002